

Tube 14x11 mm carbon-vinylepoxy 456 ARTICLE NR: **CT01411**

Technical data

calculated values

Outside diameter max	14,1	mm
Outside diameter min	13,7	mm
Wall thickness	1,5	mm
Wall thickness maximum	1,65	mm
Wall thickness minimum	1,35	mm
Tensile strength (mpa)	2050	Mpa
Tensile modulus	117	Gpa
Fiber volume content	51	%
Tg (DSC)	80	°C
Straightness (total)		
2 meter	3	mm
4 meter	7	mm
6 meter	9	mm
Fiber	carbon	
Resin	Vinylepoxy	
Weight	89	gram/m
Internal braiding	Yes	
90v Winding	Yes	
37° Braiding	No	
Undirectional	Yes	

Other standards in accordance with NEN-EN 13706